



Amendments to the Claims:

The following listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) A method for polishing a glass hard disk platter, comprising polishing a glass hard disk platter using a stable slurry in which cerium(IV) oxide particles having an average secondary particle size of 0.1 to 0.5  $\mu\text{m}$  are dispersed in water and which contains  $\text{CeO}_2$  in a concentration of 0.2 to 30 wt%, wherein a proportion of cerium expressed as a ratio of (cerium oxide)/(cerium oxide + other rare earth oxides) in the cerium(IV) oxide particles is 95% or more based on weight, and the stable slurry is a slurry of surface-modified cerium(IV) oxide obtained by heat-treating cerium(IV) oxide that is obtained by blowing oxygen or a gas containing oxygen into a suspension obtained by reacting a cerium (III) salt with an alkaline substance in a (OH)/(Ce<sup>3+</sup>) molar ratio of 3 to 30, in an aqueous medium in the presence of an ammonium salt having a non-oxidative anionic component selected from the group consisting of ammonium carbonate, ammonium hydrogen carbonate, and mixtures thereof.

2. (Canceled)

3. (Original) The method according to claim 1, wherein a specific surface area of the cerium(IV) oxide particles is 2 to 200  $\text{m}^2/\text{g}$ .

4. (Canceled)

5. (New) The method according to claim 1, wherein the cerium (III) salt and the alkaline substance are reacted under an inert gas atmosphere.

6. (New) The method according to claim 1, wherein the cerium (III) salt and the alkaline substance are reacted at an atmospheric pressure.